

Alliance Specialty Products

High Performance Polymers

ASP 221LTC

Low Temperature Cure Epoxy PRODUCT DATA SHEET

Product Description

ASP 221LTC is a 100% solids epoxy designed for application at low temperature. Exhibits good clarity, low blush, and excellent cure down to 32° F. ASP 221LTC offers excellent chemical resistance and has a low blush cure.

Product Features

- May be used as a binder for troweled or decorative floor systems.
- Fast low temperature setting characteristics allow for multiple coats.
- Good clarity and chemical resistance
- Positive cures at temperatures from 32° to 60° F.

Uses

- Showers
- Kitchens
- Restrooms
- Industrial Facilities

Coverage

- 200 square feet per gallon yields 8.0 mils DFT.
- Two coats are recommended for general use.

Installation Guide

-Preparation

- Surface must be properly prepared, consult ASP Concrete Preparation Bulletin for details.
- Surface must be properly primed.

-Mixing

- Observe all precautions on the MSDS and label when using ASP products.
- Mix 2 parts resin, (part A), with 1 part hardener, (part B).
- Mix using a slow speed drill for at least 2 minutes.

-Application

- Apply with either a good quality, medium nap roller or a nylon or natural bristle brush.

- Consult ASP Product Selection Guide for more information.

-Cure

- Re-coat: 16 hours at 50° F, shorter times may affect gloss.
- Human traffic: 8-12 hours.
- Full chemical cure: 5 days.

-Clean-Up

- Clean skin with soap and water.
- Use MEK or proprietary epoxy thinners for equipment.

Packing

Unit	Part A	Part B
3 gal	1 x 2	1 x 1
15 gal	2 x 5	1 x 5
150 gal	2 x 50	1 x 50

Properties

Composition:	Two component, cycloaliphatic amine adduct cured epoxy
Color:	Clear
Gloss: @ 60°	100
Weight/gal:	8.87lbs, mixed
Solids Content:	100%
Mix Ratio:	2A:1B by volume
Pot Life:	4 minutes at 70° F
Viscosity:	~1000 cps, mixed
Tensile Strength:	7400 psi
Elongation:	2.5%
Adhesion to Concrete:	350 psi (concrete fails)
Hardness:	80 (Shore D)
Abrasion Resistance:	35-40mg loss -CS-17 wheel, 1kg load, 1000 cycles Service
Service Temperature:	175° F(immersion) 225° F(dry heat)

Alliance Specialty Products

High Performance Polymers

ASP 221LTC

Low Temperature Cure Epoxy

PRODUCT DATA SHEET

Safety

- MSDS are available from ASP and should be consulted prior to use of this product.
- This product is intended for use by professionals only.
- Keep away from children and those not trained in the use of this product and the potential hazards.
- **ASP 221LTC** is a two component epoxy system. Part A contains epoxy resin; part B contains cycloaliphatic amine adduct.
- Workers should wear gloves and goggles when mixing or applying product.
- Clean up with soap and warm water.
- Be sure to follow all label and MSDS cautions.

Warranty

ASP warrants its products to be free of defects and conform to manufacturing standards for a maximum period of one year. ASP will replace the product or refund the purchase price at ASP's discretion. Buyer expressly waives claim to additional damages. Any warranty claim must be made in writing no later than one year from the noncomplying product's purchasing date. No one, including, but not exclusively, distributors, representatives, or applicators, may make modifications to the product data or warranty or extend any form of oral warranty on behalf of ASP.

Important Notice

There are no other warranties by ASP of any nature whatsoever other than those printed herein, expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Buyer agrees that seller assumes no liability for incidental or consequential damages of any kind from the use or misuse of the product. Preceding information is based on data collected by ASP and is believed to be accurate. The Buyer is responsible for making the decision as to the suitability of the product for a particular purpose.