## **Alliance Specialty Products**

High Performance Polymers

### **ASP 421PUC**

# Pigmented Undercoat Epoxy PRODUCT DATA SHEET

#### **Product Description**

ASP 421PUC is a 100% solids, general use epoxy resin used as a binder and coating in both industrial and decorative flooring systems. ASP 421PUC is a lightly pigmented epoxy, ideal for use under pigmented epoxies or urethanes.

#### **Product Features**

- Slightly pigmented for use in pigmented floors.
- Contains no water or solvents.
- Odorless, allowing for use in occupied facilities.
- USDA approved for food handling facilities.
- Stain resistant, minimal maintenance finish.
- User friendly mix ratio with a moderate cure time.

#### Uses

- · Locker Rooms
- Food Service
- Restrooms
- · Industrial Facilities
- · New or rehabilitated concrete

#### **Coverage**

- 200 square feet per gallon yields 8.0 mils DFT.
- Two coats are recommended for general use.

#### **Installation Guide**

- -Preparation
- Surface must be properly prepared, consult ASP Concrete Preparation Bulletin for details.
- Surface must be primed with either ASP 321 Epoxy Primer or 421PUC if conditions permit.
- Minimum application surface temperature is 50° F, preferred 65-75° F.

#### -Mixing

· Observe all precautions on the

MSDS and label when using ASP products.

- Mix 4 parts resin, (part A), with 1 part hardener, (part B).
- Mix using a slow speed drill for at least 2 minutes.

#### -Application

- Apply with either a good quality, medium nap roller or a nylon or natural bristle brush.
- Consult ASP Product Selection Guide for more information.

#### -Cure

- Re-coat: 16 hours at 70° F, shorter times may affect gloss.
- Light human traffic: 8-12 hours.
- Full chemical cure: 5 days.

#### -Clean-Up

- · Clean skin with soap and water.
- Use MEK or proprietary epoxy thinners for equipment.

<u>Properties</u>		
Composition:	Two component, amine adduct cured epoxy	
Color:	ASP Standard Colors	
Gloss: @ 60°	100	
Weight/gal:	8.87lbs, mixed	
Solids Content:	100%	
Mix Ratio:	4A:1B by volume	
Pot Life:	20 minutes at 70° F	
Viscosity:	~950 cps, mixed	
Tensile Strength:	8500 psi	
Elongation:	5.5%	
Adhesion to Concrete:	350 psi (concrete failure)	
Hardness:	80 (Shore D)	
Abrasion Resistance:	35-40mg loss -CS-17 wheel, 1kg load, 1000 cycles Service	
Service	160° F(immersion)	

<b>Packing</b>		
Unit	Part A	Part B
5 gal	4 gal	1 gal
25 gal	4x5 gal	1x5 gal
250 gal	4x50 gal	1x50 gal

Temperature:

180° F(dry heat)

## **Alliance Specialty Products**

High Performance Polymers

### **ASP 421PUC**

# Pigmented Undercoat Epoxy PRODUCT DATA SHEET

#### **Safety**

- MSDS are available from ASP and should be consulted prior to use of this product.
- This product is intended for use by professionals only.
- Keep away from children and those not trained in the use of this product and the potential hazards.
- ASP 421PUC is a two component epoxy system. Part A contains epoxy resin; part B contains amine epoxy adduct.
- Workers should wear gloves and goggles when mixing or applying product.
- Clean up with soap and warm water.
- Be sure to follow all label and MSDS cautions.

#### **Warranty**

ASP warrants its products to be free of defects and conform to manufacturing standards for a maximum period of one year. ASP will replace the product or refund the purchase price at ASP's discretion. Buyer expressly waives claim to additional damages. Any warranty claim must be made in writing no later than one year from the noncomplying product's purchasing date. No one, including, but not exclusively, distributors, representatives, or applicators, may make modifications to the product data or warranty or extend any form of oral warranty on behalf of ASP.

#### **Important Notice**

There are no other warranties by ASP of any nature whatsoever other than those printed herein, expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. Buyer agrees that seller assumes no liability for incidental or consequential damages of any kind from the use or misuse of the product. Preceding information is based on data collected by ASP and is believed to be accurate. The Buyer is responsible for making the decision as to the suitability of the product for a particular purpose.